

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	7100	MPa	ISO 527
Stress at break	90	MPa	ISO 527
Strain at break	14	%	ISO 527
Flexural strength	110	MPa	ISO 178
Charpy impact strength, +23°C	35	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	223	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	200	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	215	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	42	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	102	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	2	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	3.6	-	IEC 62631-2-1
Dissipation factor, 1MHz	170	E-4	IEC 62631-2-1
Volume resistivity	1E14	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Water absorption	0.32	%	Sim. to ISO 62
Humidity absorption	0.13	%	Sim. to ISO 62
Density	1550	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100 - 120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.04	%	-
Melt temperature	250 - 275	°C	-
Mold temperature	60 - 100	°C	-

Characteristics

Processing

Injection Molding

Special Characteristics

Flame retardant, Halogen-free

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa