

BESTDUR TXG6 /02

PBT-GF30

Grupo Triesa

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	9000	MPa	ISO 527
Tensile Strength	135	MPa	ISO 527
Strain at break	3	%	ISO 527
Charpy impact strength, +23°C	40	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	205	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	220	°C	ISO 75-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Electrical properties			
ISO Data			
Surface resistivity	1E15	Ohm	IEC 62631-3-2
Electric strength	29	kV/mm	IEC 60243-1
Comparative tracking index	260	-	IEC 60112
Other properties			
Water absorption	0.1	%	Sim. to ISO 62
Density	1640	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Black

Special Characteristics

Flame retardant

Applications

Electrical and Electronical

Regional Availability

Europe