

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.6	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	10700	MPa	ISO 527
^[C] Stress at break	140	MPa	ISO 527
^[C] Strain at break	2	%	ISO 527
^[C] Charpy notched impact strength, +23°C	7.2	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	184	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	217	°C	ISO 75-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Electric strength	18	kV/mm	IEC 60243-1

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1430	kg/m ³	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	121	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	235 - 265	°C	-
Mold temperature	65 - 93	°C	-

Characteristics

Processing

Injection Molding

Additives

Release agent

Delivery form

Pellets

Regional Availability

North America

Other text information

Injection molding

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-30°F (-34°C) at 250°F (121°C) for minimum 4 hours.
 Rear Temperature 450-480 (230-250) deg F (deg C)
 Center Temperature 460-490(235-255) deg F (deg C)
 Front Temperature 470-500 (240-260) deg F (deg C)
 Nozzle Temperature 480-510 (250-265) deg F (deg C)
 Melt Temperature 460-510 (235-265) deg F (deg C)
 Mold Temperature 150-200(65-93) deg F (deg C)

Back Pressure 0-50 psi
Screw Speed Medium
Injection Speed Fast

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.