

LUPOY GP5300

(PC+ABS)-GF30

LG Chem

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1.5	g/10min	ASTM D 1238
Temperature	250	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	111	MPa	ASTM D 638
Elongation at Break	1.5	%	ASTM D 638
Flexural Modulus	7554	MPa	ASTM D 790
Flexural Strength	167	MPa	ASTM D 790
Izod Impact unnotched, 1/8 in	88.3	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 264 psi	117	°C	ASTM D 648
Other properties			
Density	1330	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	75 - 85	°C	-
Pre-drying - Time	3 - 5	h	-
Processing humidity	≤0.02	%	-
Melt temperature	235 - 265	°C	-
Mold temperature	50 - 80	°C	-
Zone 1	220 - 240	°C	-
Zone 2	235 - 255	°C	-
Zone 3	250 - 265	°C	-
Nozzle temperature	250 - 265	°C	-
Screw speed	40 - 70	rpm	-
Back pressure	0.002 - 0.006	MPa	-

Characteristics**Processing**

Injection Molding

Applications

IT / Business Machine, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America