

RamSter PF300G6BK10-L

PBT-GF30

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
Other Standards^[S]			
Molding shrinkage, parallel	0.3	%	Producer Method
Molding shrinkage, normal	1.0	%	Producer Method

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	9550	MPa	ISO 527
Tensile Strength	128	MPa	ISO 527
Strain at break	2.5	%	ISO 527
Flexural modulus, 23°C	8450	MPa	ISO 178
Flexural strength	200	MPa	ISO 178
Charpy impact strength, -30°C	55	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, -30°C	6.6	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	10.5	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	200	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	220	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Water absorption	0.4	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1530	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.02	%	-
Mold temperature	70 - 90	°C	-
Feed temperature	40 - 60	°C	-
Zone 1	245 - 255	°C	-
Zone 2	245 - 255	°C	-
Zone 3	250 - 260	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Black

Certifications

RoHS compliant

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa