

EMI 2561 FR

(PC+ABS)-MEF(x)10

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.005	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	2758	MPa	ASTM D 638
Tensile Strength	62.1	MPa	ASTM D 638
Elongation at Break	5	%	ASTM D 638
Flexural Modulus	3103	MPa	ASTM D 790
Flexural Strength	110	MPa	ASTM D 790
Izod Impact notched, 1/8 in	42.7	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.59	mm	-
Electrical properties			
ASTM Data			
Surface Resistivity	100000	Ohm	ASTM D 257
Volume Resistivity	100	Ohm*cm	ASTM D 257
Other properties			
Density	1390	kg/m ³	ASTM D 792
Moisture Content	0.02	%	-
Processing Recommendation Injection Molding			
Pre-drying - Temperature	93.3	°C	-
Pre-drying - Time	4	h	-
Melt temperature	243 - 274	°C	-
Mold temperature	51.7 - 93.3	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Increased electrical conductivity, Flame retardant

Features

EMI Attenuation/Shielding

Regional Availability

North America, Europe, Asia Pacific