

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3100	MPa	ISO 527
^[C] Yield stress	55	MPa	ISO 527
^[C] Yield strain	4	%	ISO 527
^[C] Charpy impact strength, +23°C	3.1	kJ/m ²	ISO 179/1eU

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3

[C]: CAMPUS