

Multilon® DN-3720F

(PC+ABS)-MX

Teijin Chemicals Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.4	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	6100	MPa	ISO 527
Stress at break	60	MPa	ISO 527
Strain at break	5	%	ISO 527
Flexural modulus, 23°C	5400	MPa	ISO 178
Flexural strength	100	MPa	ISO 178
Charpy impact strength, +23°C	60	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	4	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	83	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	95	°C	ISO 75-1/-2
Vicat softening temperature, B	98	°C	ISO 306
Coeff. of linear therm. expansion, parallel	30	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	65	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	V-1	class	IEC 60695-11-10
Thickness tested	1.0	mm	-
Burning behav. 5V at thickness h	5VB	class	IEC 60695-11-20
Thickness tested	1.8	mm	-
Electrical properties			
ISO Data			
Surface resistivity	1E16	Ohm	IEC 62631-3-2
Other properties			
Density	1340	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	5 - 8	h	-
Melt temperature	230 - 270	°C	-
Mold temperature	50 - 70	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Special Characteristics

Flame retardant, Halogen-free

Applications

IT / Business Machine

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa