

KM6095

PBT

KMI Group, Inc.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	40	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	55	MPa	ASTM D 638
Elongation at Break	100	%	ASTM D 638
Flexural Strength	82	MPa	ASTM D 790

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	222	°C	ASTM D 3418

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Dielectric Strength, Short Time	2	kV/mm	ASTM D 149

Other properties	Value	Unit	Test Standard
Density	1310	kg/m ³	ASTM D 792

Characteristics**Regional Availability**

North America, Asia Pacific, South and Central America, Near East/Africa