

Matrixx 34N2006

PBT

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.012	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	48.3	MPa	ASTM D 638
Flexural Modulus	2000	MPa	ASTM D 790
Gardner Impact	36.2	J	ASTM D 2794,4226,5420
Izod Impact notched, 1/8 in	530	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 66 psi	107	°C	ASTM D 648
DTUL @ 264 psi	73.9	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1350	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Pellets

Regional Availability

North America

Special Characteristics

Flame retardant