

RTP 2599 X 131264 A

(PC+ABS)-X

RTP Company

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|--------|-------|---------------|
| ASTM Data | | | |
| Mold Shrinkage, MD | 0.0025 | mm/mm | ASTM D 955 |

| Mechanical properties | Value | Unit | Test Standard |
|-----------------------------|-------|------|---------------|
| ASTM Data | | | |
| Tensile Modulus | 6895 | MPa | ASTM D 638 |
| Tensile Strength | 88.3 | MPa | ASTM D 638 |
| Flexural Modulus | 6895 | MPa | ASTM D 790 |
| Flexural Strength | 141 | MPa | ASTM D 790 |
| Izod Impact notched, 1/8 in | 69.4 | J/m | ASTM D 256 |

| Thermal properties | Value | Unit | Test Standard |
|--------------------|-------|------|---------------|
| ASTM Data | | | |
| DTUL @ 264 psi | 122 | °C | ASTM D 648 |

| Electrical properties | Value | Unit | Test Standard |
|-----------------------|-------|--------|---------------|
| ASTM Data | | | |
| Surface Resistivity | 10000 | Ohm | ASTM D 257 |
| Volume Resistivity | 10 | Ohm*cm | ASTM D 257 |

| Other properties | Value | Unit | Test Standard |
|------------------|-------|-------------------|---------------|
| Density | 1310 | kg/m ³ | ASTM D 792 |
| Moisture Content | 0.02 | % | - |

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|---|-------------|------|---------------|
| Pre-drying - Temperature | 93.3 | °C | - |
| Pre-drying - Time | 4 | h | - |
| Melt temperature | 243 - 274 | °C | - |
| Mold temperature | 51.7 - 93.3 | °C | - |
| Injection pressure | 68.9 - 103 | MPa | - |

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Features

EMI Attenuation/Shielding