

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	22	cm <sup>3</sup> /10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2900	MPa	ISO 527
<sup>[C]</sup> Yield stress	50	MPa	ISO 527
<sup>[C]</sup> Yield strain	3.3	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	80	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	8	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	105	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	120	°C	ISO 306
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	1250	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

## Characteristics

### Processing

Injection Molding

### Delivery form

White

### Special Characteristics

Heat stabilized or stable to heat

### Features

Light Blocking

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa