

**Product Texts**

Polyether block amide **Pebax® 5533 SP 01 resin** is a thermoplastic elastomer made of flexible polyether and rigid polyamide. This SP grade has been developed to be heat and UV resistant.

**Main applications:**

- Athletic foot wear components
- Ski shoes
- High performance power transmission belts

**Packaging:**

This grade is delivered dried in sealed packaging (20 or 25 kg bags) ready to be processed.

**Shelf Life:**

Two years from the delivery. For any use above this limit, please refer to our technical services.

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>170 / 161</b>	MPa	ISO 527
<sup>[C]</sup> Yield stress	<b>12 / 12</b>	MPa	ISO 527
<sup>[C]</sup> Yield strain	<b>25 / 25</b>	%	ISO 527
<sup>[C]</sup> Nominal strain at break	<b>&gt;50 / &gt;50</b>	%	ISO 527
<sup>[C]</sup> Stress at 10% elongation	<b>10 / *</b>	MPa	ISO 527
<sup>[C]</sup> Stress at 100% elongation	<b>14 / *</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break TPE	<b>52 / *</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break TPE	<b>&gt;300 / *</b>	%	ISO 527
<sup>[C]</sup> Compression set at 23 °C, 24h	<b>43 / *</b>	%	ISO 815
<sup>[C]</sup> Tear strength	<b>106 / *</b>	kN/m	ISO 34-1
<sup>[C]</sup> Abrasion resistance	<b>47 / *</b>	mm <sup>3</sup>	ISO 4649
<sup>[C]</sup> Shore D hardness	<b>50 / *</b>	-	ISO 7619-1

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>159 / *</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>66 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	<b>66 / *</b>	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	<b>170 / *</b>	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

<b>Electrical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	<b>9 / -</b>	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	<b>5 / -</b>	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	<b>1110 / -</b>	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	<b>1020 / -</b>	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	<b>3.2E11 / -</b>	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	<b>* / 3E12</b>	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	<b>38.5 / -</b>	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	<b>* / 600</b>	-	IEC 60112

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Water absorption	<b>1.2 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>0.6 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1010 / 1010</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	<b>65 - 75</b>	°C	-
Pre-drying - Time	<b>4 - 6</b>	h	-
Melt temperature	<b>200 - 270</b>	°C	-
Mold temperature	<b>25 - 60</b>	°C	-

**Characteristics**

**Processing**

Injection Molding, Film Extrusion, Profile Extrusion, Other Extrusion, Transfer Molding, Casting, Thermoforming

**Special Characteristics**

Platable, Light stabilized or stable to light, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

**Delivery form**

Pellets

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Other text information**

**Injection molding**

**Processing conditions:**

- Typical melt temperature (Min / Recommended / Max) : 200°C / 240°C / 270°C.
- Typical mold temperature : 25 – 60°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 65-75°C.

**Other extrusion**

**Processing conditions:**

- Typical melt temperature (Min / Recommended / Max) : 210°C / 220°C / 230°C
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 65-75°C