

RamSter PF103WT252

PBT

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	23	g/10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
Other Standards^[S]			
Molding shrinkage, parallel	1.7	%	Producer Method
Molding shrinkage, normal	1.9	%	Producer Method

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2600	MPa	ISO 527
Tensile Strength	58	MPa	ISO 527
Yield strain	10	%	ISO 527
Strain at break	25	%	ISO 527
Flexural modulus, 23°C	2250	MPa	ISO 178
Flexural strength	90	MPa	ISO 178
Izod notched impact strength, +23°C	6	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	50	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Water absorption	0.34	%	Sim. to ISO 62
Humidity absorption	0.08	%	Sim. to ISO 62
Density	1310	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.02	%	-
Mold temperature	70 - 90	°C	-
Feed temperature	40 - 60	°C	-
Zone 1	235 - 255	°C	-
Zone 2	235 - 255	°C	-
Zone 3	240 - 260	°C	-

Characteristics**Processing**

Injection Molding

Certifications

RoHS compliant

Delivery form

White

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa