

AKROLOY® PA ICF 20 black (5268)

(PA66+PA6I/6T)-CF20

Akro-Plastic GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	40	cm ³ /10min	ISO 1133
Temperature	275	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	17000	MPa	ISO 527
Stress at break	200	MPa	ISO 527
Strain at break	2	%	ISO 527
Flexural modulus, 23°C	13000	MPa	ISO 178
Flexural strength	250	MPa	ISO 178
Charpy impact strength, +23°C	45	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	35	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	5	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	255	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	223	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Other properties	Value	Unit	Test Standard
Density	1230	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	320	°C	-
Mold temperature	100	°C	-
Injection pressure	75	MPa	-

Characteristics**Processing**

Injection Molding

Features

Tribologic Grade

Delivery form

Black

Regional Availability

Europe, Asia Pacific