

RTP 1000 HI FR A

PBT

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.02	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2068	MPa	ASTM D 638
Tensile Strength	42.7	MPa	ASTM D 638
Flexural Modulus	2206	MPa	ASTM D 790
Flexural Strength	68.9	MPa	ASTM D 790
Izod Impact notched, 1/8 in	107	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.59	mm	-
DTUL @ 66 psi	149	°C	ASTM D 648
DTUL @ 264 psi	65.6	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1350	kg/m ³	ASTM D 792
Moisture Content	0.03	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	121	°C	-
Pre-drying - Time	4	h	-
Melt temperature	238 - 271	°C	-
Mold temperature	79.4 - 107	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Flame retardant, High impact or impact modified