

**AKROLOY® PA CF 40 black (3639)**

(PA66+PA6I/6T)-CF40

Akro-Plastic GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	30000	MPa	ISO 527
Stress at break	260	MPa	ISO 527
Strain at break	1.5	%	ISO 527
Flexural modulus, 23°C	28500	MPa	ISO 178
Flexural strength	380	MPa	ISO 178
Charpy impact strength, +23°C	55	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	45	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	7	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	6	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	255	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	220	°C	ISO 75-1/-2
Temp. of deflection under load, 8.00 MPa	110	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Other properties	Value	Unit	Test Standard
Density	1330	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	320	°C	-
Mold temperature	100	°C	-
Injection pressure	75	MPa	-

**Characteristics****Processing**

Injection Molding

**Features**

Tribologic Grade

**Delivery form**

Black

**Regional Availability**

Europe, Asia Pacific