

SLOVASTER® C FRU 2

PBT

Plastcom, spol. s r.o.

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|--------------|-------------------|----------------------|
| ISO Data | | | |
| Melt flow index, MFI | 15 | g/10min | ISO 1133 |
| Temperature | 250 | °C | - |
| Load | 2.16 | kg | - |
| Molding shrinkage, parallel | 0.6 | % | ISO 294-4, 2577 |
| Molding shrinkage, normal | 0.7 | % | ISO 294-4, 2577 |
| Mechanical properties | | | |
| ISO Data | | | |
| Tensile Modulus | 2700 | MPa | ISO 527 |
| Tensile Strength | 65 | MPa | ISO 527 |
| Flexural modulus, 23°C | 2600 | MPa | ISO 178 |
| Charpy impact strength, +23°C | N | kJ/m ² | ISO 179/1eU |
| Thermal properties | | | |
| ISO Data | | | |
| Melting temperature, 10°C/min | 240 | °C | ISO 11357-1/-3 |
| Temp. of deflection under load, 1.80 MPa | 96 | °C | ISO 75-1/-2 |
| Vicat softening temperature, B | 110 | °C | ISO 306 |
| Burning behav. at thickness h | V-0 | class | IEC 60695-11-10 |
| Thickness tested | 1.0 | mm | - |
| Electrical properties | | | |
| ISO Data | | | |
| Comparative tracking index | 250 | - | IEC 60112 |
| Other properties | | | |
| Density | 1200 | kg/m ³ | ISO 1183 |
| Moisture Content | 0.1 | % | - |

Characteristics**Processing**

Injection Molding

Delivery form

Natural Color

Special Characteristics

Flame retardant

Applications

Automotive, Electrical and Electronical

Regional Availability

Europe