

**SLOVASTYR® B BT N**

PBT

Plastcom, spol. s r.o.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>2000</b>	MPa	ISO 527
Tensile Strength	<b>50</b>	MPa	ISO 527
Flexural modulus, 23°C	<b>2000</b>	MPa	ISO 178
Charpy impact strength, +23°C	<b>25</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>2</b>	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>210</b>	°C	ISO 11357-1/-3

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1310</b>	kg/m <sup>3</sup>	ISO 1183
Moisture Content	<b>0.15</b>	%	-

**Characteristics****Processing**

Injection Molding

**Certifications**

Recycled Resin Content

**Delivery form**

Natural Color

**Regional Availability**

Europe