

SPESIN® KP212G30V0BLS

PBT-GF30

Kolon Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0085	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	138	MPa	ISO 527
Flexural modulus, 23°C	9190	MPa	ISO 178
Charpy notched impact strength, +23°C	6.6	kJ/m ²	ISO 179/1eA
Rockwell hardness	R 120	-	ISO 2039-2
ASTM Data			
Tensile Strength	132	MPa	ASTM D 638
Flexural Modulus	8826	MPa	ASTM D 790
Flexural Strength	206	MPa	ASTM D 790
Rockwell Hardness	R 120	-	ASTM D 785
Izod Impact notched, 1/8 in	78	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	224	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	200	°C	ISO 75-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.8	mm	-
Coefficient of Thermal Expansion, MD	40	E-6/K	ASTM D 696
DTUL @ 66 psi	220	°C	ASTM D 648
DTUL @ 264 psi	200	°C	ASTM D 648
Melting Temperature	224	°C	ASTM D 3418

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Dielectric Strength, Short Time	27	kV/mm	ASTM D 149
Dielectric Constant, 1 MHz	3.7	-	ASTM D 150
Arc Resistance	110	s	ASTM D 495

Other properties	Value	Unit	Test Standard
Density	1630	kg/m ³	ISO 1183
Density	1630	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100 - 120	°C	-
Pre-drying - Time	3 - 5	h	-
Processing humidity	≤0.05	%	-
Mold temperature	60 - 80	°C	-
Zone 1	240	°C	-
Zone 2	245	°C	-
Zone 3	250	°C	-
Nozzle temperature	250	°C	-

Characteristics**Processing**

Injection Molding

Chemical Resistance

Hydrolytically Stable

Delivery form

Black

Regional Availability

North America, Asia Pacific

Special Characteristics

Flame retardant