

Vampter 3028 V0

PBT-GF30

VAMP TECH SPA

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Izod impact strength, +23°C	35	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	5.5	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	11000	MPa	ASTM D 638
Tensile Strength at Yield	85	MPa	ASTM D 638
Elongation at Break	1.7	%	ASTM D 638

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.2	mm	-
ASTM Data			
Vicat Temperature	200	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	1530	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	110	°C	-
Pre-drying - Time	3	h	-
Melt temperature	250	°C	-
Mold temperature	90	°C	-

Characteristics**Processing**

Injection Molding

Certifications

RoHS compliant

Special Characteristics

Flame retardant, Halogen-free

Regional Availability

Europe