

CELSTRAN® PBT-GF50-08

PBT-GLF50

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	16640	MPa	ISO 527
^[C] Stress at break	178	MPa	ISO 527
^[C] Strain at break	1.45	%	ISO 527
^[C] Charpy notched impact strength, +23°C	32	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1730	kg/m ³	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Melt temperature	280 - 300	°C	-
Mold temperature	80 - 90	°C	-

Characteristics**Processing**

Injection Molding

Features

Long fiber reinforced

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific

Other text information**Injection molding**

PBT Drying Requirements: 4 hrs. @ 120° C.

A dehumidifier or desiccant dryer is recommended.

Celstran can be processed on a standard injection molding unit.

A general purpose metering screw is recommended with a zone distribution of 40% feed, 40% transition, and 20% metering.

A free flowing check ring assembly is recommended.

Melt Temp.: 280 - 300° C.

Mold Temp.: 80 - 90° C.