

Witcom PBT/2S

PBT-MEF(x)

Wittenburg B.V.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.2	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	55	MPa	ISO 527
Strain at break	10	%	ISO 527
Flexural modulus, 23°C	2400	MPa	ISO 178
Flexural strength	80	MPa	ISO 178
Izod impact strength, +23°C	50	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	5	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	65	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	120	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1000000	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Water absorption	0.45	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1390	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Increased electrical conductivity

Regional Availability

Europe