

EMI 1062

PBT-MEF(x)15

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0125	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	3103	MPa	ASTM D 638
Tensile Strength	58.6	MPa	ASTM D 638
Flexural Modulus	3034	MPa	ASTM D 790
Flexural Strength	93.1	MPa	ASTM D 790
Izod Impact notched, 1/8 in	37.4	J/m	ASTM D 256
Electrical properties			
ASTM Data			
Surface Resistivity	10000	Ohm	ASTM D 257
Volume Resistivity	1	Ohm*cm	ASTM D 257
Other properties			
Density	1490	kg/m ³	ASTM D 792
Moisture Content	0.03	%	-
Processing Recommendation Injection Molding			
Pre-drying - Temperature	121	°C	-
Pre-drying - Time	4	h	-
Melt temperature	193 - 221	°C	-
Mold temperature	62.8 - 82.2	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Features

EMI Attenuation/Shielding

Special Characteristics

Increased electrical conductivity

Regional Availability

North America, Europe, Asia Pacific