

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	14	g/10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	1.5	%	ISO 294-4, 2577
Molding shrinkage, normal	1.5	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	7400	MPa	ISO 527
Tensile Strength	60	MPa	ISO 527
Strain at break	1.7	%	ISO 527
Charpy impact strength, +23°C	23	kJ/m ²	ISO 179/1eU

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	60	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	167	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	59	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	59	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10

Electrical properties	Value	Unit	Test Standard
Other Standards^[5]			
Volume resistivity	3.1E12	Ohm*m	IEC 61340-2-3
Surface resistivity	4.5E12	Ohm	IEC 61340-2-3

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Humidity absorption	0.1	%	Sim. to ISO 62
Density	1730	kg/m ³	ISO 1183
Bulk density	920	kg/m ³	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	3 - 6	h	-
Processing humidity	≤0.02	%	-
Melt temperature	270 - 280	°C	-
Mold temperature	130	°C	-
Zone 1	240 - 290	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets, White

Special Characteristics

Thermally Conductive

Applications

Automotive, Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America