

RamSter PF350M3OR24

PBT-MX15

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	23.8	cm ³ /10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
Other Standards^[S]			
Molding shrinkage, parallel	0.9	%	Producer Method

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3600	MPa	ISO 527
Tensile Strength	62	MPa	ISO 527
Yield strain	7.2	%	ISO 527
Izod notched impact strength, +23°C	4.4	kJ/m ²	ISO 180/1A

Other properties	Value	Unit	Test Standard
Humidity absorption	0.3	%	Sim. to ISO 62
Density	1420	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100 - 120	°C	-
Pre-drying - Time	2 - 3	h	-
Processing humidity	≤0.02	%	-
Mold temperature	80 - 120	°C	-
Feed temperature	60 - 80	°C	-
Zone 1	240 - 260	°C	-
Zone 2	260 - 280	°C	-
Zone 3	280 - 300	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

U.V. stabilized or stable to weather

Certifications

RoHS compliant

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa