

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.1	%	ISO 294-4, 2577
Molding shrinkage, normal	1.1	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	3400	MPa	ISO 527
Stress at break	25	MPa	ISO 527
Strain at break	0.7	%	ISO 527
Charpy impact strength, +23°C	10	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	1.2	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	70	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	165	°C	ISO 75-1/-2
Vicat softening temperature, B	180	°C	ISO 306
Electrical properties			
ASTM Data			
Surface Resistivity	1E12	Ohm	ASTM D 257
Other properties			
Density	1000	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	120 - 130	°C	-
Pre-drying - Time	3	h	-
Melt temperature	230 - 250	°C	-
Mold temperature	70 - 90	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

Europe