

Product Texts

PA66 Blend with partial aromatic share, 50% glass fiber content and heat stabilizer improved flow characteristics. For all kind of injection molding parts with high requirements on strength.

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	16500 / 15500	MPa	ISO 527
Stress at break	235 / 210	MPa	ISO 527
Strain at break	3 / 3	%	ISO 527
Charpy impact strength, -30°C	94 / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	15 / 15	kJ/m ²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	240 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	250 / *	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
Electric strength	33 / -	kV/mm	IEC 60243-1
Comparative tracking index	600 / -	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	4 / *	%	Sim. to ISO 62
Humidity absorption	1.4 / *	%	Sim. to ISO 62
Density	1560 / -	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4 - 8	h	-
Processing humidity	≤0.1	%	-
Mold temperature	80 - 120	°C	-
Feed temperature	60 - 80	°C	-
Zone 1	260 - 290	°C	-
Nozzle temperature	270 - 300	°C	-
Maximum residence time	8	min	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

Europe