

**Product Texts**

Partially aromatic PA66 blend with 50% glass fiber proportions and heat stabilized. The product tends to reduced warpage and has improved flow characteristics.

For injection-moulded components with high requirements to isotropic strength properties.

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>17500 / 16500</b>	MPa	ISO 527
Stress at break	<b>220 / 200</b>	MPa	ISO 527
Strain at break	<b>2.5 / 2.5</b>	%	ISO 527
Charpy impact strength, +23°C	<b>90 / N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>14 / 16</b>	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>260 / *</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>244 / *</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>255 / *</b>	°C	ISO 75-1/-2
Vicat softening temperature, B	<b>210 / *</b>	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	<b>HB / *</b>	class	IEC 60695-11-10
Thickness tested	<b>1.6 / *</b>	mm	-

<b>Electrical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Volume resistivity	<b>1E12 / -</b>	Ohm*m	IEC 62631-3-1
Electric strength	<b>33 / -</b>	kV/mm	IEC 60243-1
Comparative tracking index	<b>600 / -</b>	-	IEC 60112

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Water absorption	<b>4 / *</b>	%	Sim. to ISO 62
Humidity absorption	<b>1.4 / *</b>	%	Sim. to ISO 62
Density	<b>1570 / -</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Special Characteristics**

Heat stabilized or stable to heat

**Regional Availability**

Europe

**Features**

Low Warpage