

Product Texts

LNP STAT-KON DD000P compound is based on Polycarbonate (PC) resin containing conductive carbon powder. Added features of this grade include: Electrically Conductive, Exceptional Processing.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8	%	ISO 294-4, 2577
ASTM Data			
Mold Shrinkage, MD	0.7	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.8	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2800	MPa	ISO 527
Yield stress	57	MPa	ISO 527
Yield strain	4.8	%	ISO 527
Stress at break	51	MPa	ISO 527
Strain at break	9.9	%	ISO 527
Flexural modulus	2400	MPa	ISO 178
Flexural strength	78	MPa	ISO 178
Izod impact strength, +23°C, 4mm	205	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	5	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	2750	MPa	ASTM D 638
Tensile Strength at Yield	57	MPa	ASTM D 638
Tensile Strength at Break	49	MPa	ASTM D 638
Elongation at Yield	4.8	%	ASTM D 638
Elongation at Break	20.1	%	ASTM D 638
Flexural Modulus	2750	MPa	ASTM D 790
Izod Impact notched, 1/8 in	234	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	2230	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	126	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	135	°C	ISO 75-1/-2
ASTM Data			
DTUL @ 66 psi	135	°C	ASTM D 648
DTUL @ 264 psi	125	°C	ASTM D 648

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1E9	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1230	kg/m ³	ISO 1183
Water Absorption, 24hr	0.1	%	ASTM D 570
Density	1230	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	305 - 325	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	295 - 305	°C	-
Zone 2	310 - 320	°C	-

LNP™ STAT-KON™ Compound DD000P - Asia

PC-CD

Saudi Basic Industries Corporation (SABIC)

Zone 3	320 - 330	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

Asia Pacific

Special Characteristics

Increased electrical conductivity