

Product Texts

LNP STAT-KON DE003Z compound is based on Polycarbonate (PC) resin containing 15% carbon fiber. Added features of this grade include: Electrically Conductive, Extrusion grade.

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	143	°C	ISO 75-1/-2
ASTM Data			
DTUL @ 264 psi	144	°C	ASTM D 648

Characteristics**Processing**

Injection Molding

Regional Availability

Asia Pacific

Special Characteristics

Increased electrical conductivity