

Product Texts

Base Polymer	Polycarbonate
Filler/Additive System	10 % glass fibres
Market Segment	building and construction, various
Typical Applications	injection moulded parts

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	10	cm ³ /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-

[C]: CAMPUS

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3800	MPa	ISO 527
^[C] Stress at break	75	MPa	ISO 527
^[C] Strain at break	3.5	%	ISO 527
^[C] Charpy impact strength, +23°C	50	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties

	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	141	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	145	°C	ISO 306

[C]: CAMPUS

Other properties

	Value	Unit	Test Standard
^[C] Density	1260	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific, Near East/Africa

Other text information**Injection molding**

Pre-Drying Conditions	120 °C in a dry air (dessiccant) dryer for 2-3 h dependant on moisture content max. moisture content <0,02 %
Processing Injection Moulding	melt temperature 310-330 °C mould temperature 80-130 °C
Storage	dry, protected from light