

Iupilon GPX2010PH

PC-GF10

Mitsubishi Engineering-Plastics Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	16	cm ³ /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Melt flow index, MFI	17	g/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Molding shrinkage, parallel	0.4	%	ISO 294-4, 2577
Molding shrinkage, normal	0.4	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3000	MPa	ISO 527
Yield stress	55	MPa	ISO 527
Yield strain	4.8	%	ISO 527
Strain at break	10	%	ISO 527
Flexural modulus, 23°C	2800	MPa	ISO 178
Flexural strength	93	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	113	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	122	°C	ISO 75-1/-2
Burning behav. at thickness h	V-1	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-

Other properties	Value	Unit	Test Standard
Water absorption	0.14	%	Sim. to ISO 62
Density	1260	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4 - 8	h	-
Mold temperature	60 - 100	°C	-
Zone 1	280 - 300	°C	-
Zone 2	280 - 300	°C	-
Zone 3	280 - 300	°C	-
Nozzle temperature	280 - 300	°C	-

Characteristics**Processing**

Injection Molding

Additives

Flame retarding agent

Special Characteristics

Flame retardant, High impact or impact modified

Applications

IT / Business Machine, Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific