

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|--------|-------------------|---------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 11 | g/10min | ASTM D 1238 |
| Temperature | 300 | °C | - |
| Load | 1.2 | kg | - |
| Mold Shrinkage, MD | 0.0045 | mm/mm | ASTM D 955 |
| Mechanical properties | | | |
| ASTM Data | | | |
| Tensile Strength | 50.7 | MPa | ASTM D 638 |
| Flexural Modulus | 3103 | MPa | ASTM D 790 |
| Flexural Strength | 93.1 | MPa | ASTM D 790 |
| Rockwell Hardness | R 115 | - | ASTM D 785 |
| Izod Impact notched, 1/8 in | 411 | J/m | ASTM D 256 |
| Thermal properties | | | |
| ASTM Data | | | |
| UL 94 Flame rating | HB | - | UL 94 |
| Thickness tested | 1.5 | mm | - |
| DTUL @ 264 psi | 132 | °C | ASTM D 648 |
| Other properties | | | |
| Density | 1210 | kg/m ³ | ASTM D 792 |

Characteristics

Certifications

RoHS compliant

Applications

IT / Business Machine

Regional Availability

Europe, Asia Pacific