LNP™ THERMOTUF™ Compound DF002PSI

PC-GF10 Saudi Basic Industries Corporation (SABIC)

Product Texts

LNP THERMOTUF DF002PSI compound is based on Polycarbonate (PC) resin containing 10% glass fiber. Added features of this grade include: Impact Modified, High Flow, Ductile, Good Chemical Resistance.

UL Yellow Card Link E207780-103722308

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	**74**	MPa	ASTM D 638
Elongation at Break	**5.7**	%	ASTM D 638
Flexural Modulus	**3380**	MPa	ASTM D 790
Izod Impact notched, 1/8 in	**160**	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at thickness h	**HB**	class	IEC 60695-11-10
Thickness tested	**0.8**	mm	-
ASTM Data			
DTUL @ 264 psi	**127**	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	**1250**	kg/m³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	**110**	°C	-
Pre-drying - Time	**3 - 6**	h	-
Melt temperature	**285 - 310**	°C	-
Mold temperature	**80 - 110**	°C	-
Zone 1	**260 - 280**	°C	-
Zone 2	**270 - 290**	°C	-
Zone 3	**280 - 300**	°C	-
Screw speed	**50 - 90**	rpm	-
Back pressure	**0.1 - 0.3**	MPa	-

Characteristics

Processing
Injection Molding

Chemical Resistance
General Chemical Resistance

Special Characteristics
High impact or impact modified

Regional Availability
North America, Europe, Asia Pacific

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.