

Product Texts

- MVR (300 °C/1.2 kg) 15 cm³/10 min
- 10 % glass fiber reinforced
- flame retardant
- UL 94V-0/1.2 mm
- low viscosity
- easy release
- electrical/electronic
- housing parts with low wall thickness

Processing/Physical Characteristics

ISO Data

	Value	Unit	Test Standard
^[C] Melt volume-flow rate, MVR	15	cm³/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
^[C] Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.5	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties

ISO Data

	Value	Unit	Test Standard
^[C] Tensile Modulus	3900	MPa	ISO 527
^[C] Stress at break	45	MPa	ISO 527
^[C] Strain at break	10	%	ISO 527
^[C] Charpy impact strength, +23°C	100	kJ/m²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	40	kJ/m²	ISO 179/1eU
^[C] Puncture - maximum force, +23°C	3200	N	ISO 6603-2
^[C] Puncture energy, +23°C	16	J	ISO 6603-2

[C]: CAMPUS

Thermal properties

ISO Data

	Value	Unit	Test Standard
^[C] Temp. of deflection under load, 1.80 MPa	132	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	141	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	40	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	60	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	1.2	mm	-
^[C] Oxygen index	37	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties

ISO Data

	Value	Unit	Test Standard
^[C] Relative permittivity, 100Hz	3.2	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	3.2	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	10	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	90	E-4	IEC 62631-2-1
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2
^[C] Electric strength	36	kV/mm	IEC 60243-1
^[C] Comparative tracking index	175	-	IEC 60112

[C]: CAMPUS

Other properties

	Value	Unit	Test Standard
^[C] Water absorption	0.3	%	Sim. to ISO 62
^[C] Humidity absorption	0.1	%	Sim. to ISO 62
^[C] Density	1270	kg/m³	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
ISO Data			
^[C] Injection Molding, melt temperature	300	°C	ISO 294
Injection Molding, mold temperature	110	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	2 - 3	h	-
Processing humidity	≤0.02	%	-
Melt temperature	310 - 330	°C	-
Mold temperature	80 - 130	°C	-

Characteristics

Processing

Injection Molding

Additives

Release agent

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information

Injection molding

PREPROCESSING

Max. Water content: 0.01 - 0.02 %

Drying temperature: 120 °C

Drying time:

Circulating air drying oven (50 % fresh air) 4-8 h

Fresh air dryer (high speed dryer) 2-4 h

Dry air dryer 2-3 h

PROCESSING

Melt temperature: 310-330 °C

Mold temperature: 80-130 °C

Use open nozzle.