

Matrixx 50S5102

PC-GF10

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.003	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	63.4	MPa	ASTM D 638
Flexural Modulus	3380	MPa	ASTM D 790
Izod Impact notched, 1/8 in	110	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 66 psi	146	°C	ASTM D 648
DTUL @ 264 psi	141	°C	ASTM D 648
Other properties			
Density	1250	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	121	°C	-
Pre-drying - Time	4 - 6	h	-
Melt temperature	293 - 321	°C	-
Mold temperature	71 - 104	°C	-
Zone 1	282 - 310	°C	-
Zone 2	282 - 310	°C	-
Zone 3	282 - 310	°C	-
Screw speed	40 - 75	rpm	-
Back pressure	0.345 - 0.689	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America

Delivery form

Pellets