

**NIRION F10 V0**

PC-GF10

Soredi S.p.a.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>12</b>	g/10min	ASTM D 1238
Temperature	<b>300</b>	°C	-
Load	<b>1.2</b>	kg	-

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Flexural Modulus	<b>3200</b>	MPa	ASTM D 790
Flexural Strength	<b>85</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 80</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>96.1</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
Thickness tested	<b>1.6</b>	mm	-
Vicat Temperature	<b>147</b>	°C	ASTM D 1525

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1270</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Special Characteristics**

Flame retardant

**Regional Availability**

Europe