

SCANTEC PC S75R GF10 V0

PC-GF10

Polykemi AB

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.4	%	ISO 294-4, 2577
Molding shrinkage, normal	0.4	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	45	MPa	ISO 527
Strain at break	7	%	ISO 527
Flexural modulus, 23°C	3500	MPa	ISO 178
Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	131	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	140	°C	ISO 75-1/-2
Vicat softening temperature, B	143	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Yellow Card available	yes	-	-
Glow Wire Ignition Temperature (GWIT)	960	°C	IEC 60695-2-13
GWIT - thickness tested (1)	2	mm	-

Other properties	Value	Unit	Test Standard
Density	1300	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Regional Availability

Europe, Asia Pacific

Special Characteristics

Flame retardant