

Tarolon 2500 W G2 X0

PC-GF10

Taro Plast S.p.A.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3700	MPa	ISO 527
Yield stress	75	MPa	ISO 527
Stress at break	65	MPa	ISO 527
Strain at break	8	%	ISO 527
Flexural modulus, 23°C	3700	MPa	ISO 178
Charpy impact strength, +23°C	70	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	12	kJ/m ²	ISO 179/1eA
ASTM Data			
Izod Impact notched, 1/8 in	150	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	120	J/m	ASTM D 256
Temperature	-20	°C	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	135	°C	ISO 75-1/-2
Vicat softening temperature, A	152	°C	ISO 306
Vicat softening temperature, B	146	°C	ISO 306
Coeff. of linear therm. expansion, parallel	33	E-6/K	ISO 11359-1/-2
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.97	mm	-
Limiting Oxygen Index	35	%	ASTM D 2863

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Electric strength	24	kV/mm	IEC 60243-1
Comparative tracking index	175	-	IEC 60112

Other properties	Value	Unit	Test Standard
Water absorption	0.25	%	Sim. to ISO 62
Density	1270	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Flame retardant, U.V. stabilized or stable to weather

Features

Low Odor

Applications

Automotive, Electrical and Electronical

Regional Availability

Europe