

JH720 G15

PC-GF15

Kingfa Sci. & Tech.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.004	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	85	MPa	ASTM D 638
Elongation at Break	8	%	ASTM D 638
Flexural Modulus	5400	MPa	ASTM D 790
Flexural Strength	129	MPa	ASTM D 790
Rockwell Hardness	R 84	-	ASTM D 785
Izod Impact notched, 1/8 in	106	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	557	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.6	mm	-
DTUL @ 66 psi	142	°C	ASTM D 648
DTUL @ 264 psi	138	°C	ASTM D 648

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Dielectric Strength, Short Time	22	kV/mm	ASTM D 149
Surface Resistivity	1E15	Ohm	ASTM D 257
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1260	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Applications

IT / Business Machine, Electrical and Electronical

Regional Availability

Asia Pacific