

**Product Texts**

LEXAN HFD4472 is a 20% glass filled, medium flow, impact modified, injection moldable grade designed for high flow and superior surface appearance. HFD4472 has enhanced mold release, impact ductility and broad color space.

UL Yellow Card Link [E207780-101177381](https://www.ul.com/yellow-card/E207780-101177381)

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	9	cm <sup>3</sup> /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
<b>ASTM Data</b>			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	54	MPa	ISO 527
Stress at break	56	MPa	ISO 527
Strain at break	2	%	ISO 527
Charpy impact strength, +23°C, 3mm	59	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C, 3mm	59	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C, 3mm	21	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C, 3mm	13	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact strength, +23°C	47	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C, 3mm	18	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength, -30°C, 3mm	13	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Tensile Modulus	5500	MPa	ASTM D 638
Tensile Strength at Yield	54	MPa	ASTM D 638
Tensile Strength at Break	56	MPa	ASTM D 638
Elongation at Yield	2	%	ASTM D 638
Flexural Modulus	4900	MPa	ASTM D 790
Izod Impact notched, 1/8 in	190	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	800	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Vicat softening temperature, 120°C/h 50N	135	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.4	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (GWIT)	850	°C	IEC 60695-2-13
GWIT - thickness tested (1)	1	mm	-
Glow Wire Ignition Temperature (GWIT)	875	°C	IEC 60695-2-13
GWIT - thickness tested (2)	2	mm	-
Glow Wire Ignition Temperature (GWIT)	850	°C	IEC 60695-2-13
GWIT - thickness tested (3)	3	mm	-
<b>ASTM Data</b>			
DTUL @ 66 psi	132	°C	ASTM D 648
DTUL @ 264 psi	128	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Water absorption	0.12	%	Sim. to ISO 62
Humidity absorption	0.04	%	Sim. to ISO 62
Density	1330	kg/m <sup>3</sup>	ISO 1183

Density	<b>1330</b>	kg/m <sup>3</sup>	ASTM D 792
---------	-------------	-------------------	------------

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>120</b>	°C	-
Pre-drying - Time	<b>3 - 4</b>	h	-
Processing humidity	<b>≤0.02</b>	%	-
Melt temperature	<b>290 - 310</b>	°C	-
Mold temperature	<b>70 - 95</b>	°C	-
Zone 1	<b>265 - 290</b>	°C	-
Zone 2	<b>275 - 300</b>	°C	-
Zone 3	<b>290 - 310</b>	°C	-
Screw speed	<b>40 - 70</b>	rpm	-
Back pressure	<b>0.3 - 0.7</b>	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Regional Availability**

North America

**Special Characteristics**

High impact or impact modified