

**Product Texts**

LNP THERMOCOMP DF004XXC compound is based on Polycarbonate (PC) resin containing 20% glass fiber.

UL Yellow Card Link [E207780-101343857](https://www.ul.com/yellowcard/E207780-101343857)

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>6800</b>	MPa	ISO 527
Yield stress	<b>121</b>	MPa	ISO 527
Yield strain	<b>3.1</b>	%	ISO 527
Flexural modulus	<b>6100</b>	MPa	ISO 178
Izod impact strength, +23°C, 4mm	<b>65</b>	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	<b>12</b>	kJ/m <sup>2</sup>	ISO 180/1A

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>143</b>	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	<b>V-2</b>	class	IEC 60695-11-10
Thickness tested	<b>1.5</b>	mm	-
Burning behav. at thickness h	<b>V-1</b>	class	IEC 60695-11-10
Thickness tested	<b>3.0</b>	mm	-

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1360</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>120</b>	°C	-
Pre-drying - Time	<b>4</b>	h	-
Processing humidity	<b>≤0.02</b>	%	-
Melt temperature	<b>305 - 325</b>	°C	-
Mold temperature	<b>80 - 110</b>	°C	-
Zone 1	<b>295 - 305</b>	°C	-
Zone 2	<b>310 - 320</b>	°C	-
Zone 3	<b>320 - 330</b>	°C	-
Screw speed	<b>30 - 60</b>	rpm	-
Back pressure	<b>0.2 - 0.3</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific