

ML3420

PC-GF20

Cheng Yu Plastic Company Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	100	MPa	ASTM D 638
Flexural Strength	170	MPa	ASTM D 790
Rockwell Hardness	M 92	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	3	mm	-

Other properties	Value	Unit	Test Standard
Density	1350	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

Heat stabilized or stable to heat

Regional Availability

Asia Pacific

Applications

Electrical and Electronical