

Kotex KG-30F15

PC-GF30

Kotec Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.004	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Break	120	MPa	ASTM D 638
Elongation at Break	3	%	ASTM D 638
Flexural Modulus	4900	MPa	ASTM D 790
Flexural Strength	127	MPa	ASTM D 790
Izod Impact notched, 1/8 in	118	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
DTUL @ 264 psi	145	°C	ASTM D 648
Electrical properties			
ASTM Data			
Dielectric Strength, Short Time	20	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.008	-	ASTM D 150
Dielectric Constant, 1 MHz	3.2	-	ASTM D 150
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257
Arc Resistance	110	s	ASTM D 495
Other properties			
Water Absorption, 24hr	0.2	%	ASTM D 570
Density	1570	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Pellets, Natural Color

Regional Availability

Europe, Asia Pacific

Features

Low Odor