

QR Resin QR-1000-GF30 V

PC-GF30

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	15	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	131	MPa	ASTM D 638
Flexural Modulus	6890	MPa	ASTM D 790
Izod Impact unnotched, 1/8 in	1100	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	152	°C	ASTM D 648
DTUL @ 264 psi	146	°C	ASTM D 648
Other properties			
Density	1430	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	121	°C	-
Pre-drying - Time	3 - 6	h	-
Melt temperature	316 - 343	°C	-
Mold temperature	82 - 116	°C	-
Zone 1	282 - 304	°C	-
Zone 2	293 - 316	°C	-
Zone 3	304 - 338	°C	-
Nozzle temperature	304 - 338	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

U.V. stabilized or stable to weather

Delivery form

Pellets, Natural Color

Regional Availability

North America