

**Product Texts**

- MVR (300 °C/1.2 kg) 19 cm<sup>3</sup>/10 min
- improved impact strength
- low viscosity
- easy release

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	19	cm <sup>3</sup> /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.7	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2400	MPa	ISO 527
<sup>[C]</sup> Yield stress	62	MPa	ISO 527
<sup>[C]</sup> Yield strain	5.8	%	ISO 527
<sup>[C]</sup> Nominal strain at break	>50	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Puncture - maximum force, +23°C	4900	N	ISO 6603-2
<sup>[C]</sup> Puncture - maximum force, -30°C	5800	N	ISO 6603-2
<sup>[C]</sup> Puncture energy, +23°C	50	J	ISO 6603-2
<sup>[C]</sup> Puncture energy, -30°C	55	J	ISO 6603-2

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	123	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	136	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	143	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	65	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	65	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Oxygen index	30	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	3.1	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	3	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	10	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	110	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	>1E15	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	34	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	250	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Water absorption	0.3	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	0.12	%	Sim. to ISO 62
<sup>[C]</sup> Density	1200	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Injection Molding, melt temperature	<b>280</b>	°C	ISO 294
Injection Molding, mold temperature	<b>80</b>	°C	ISO 294
Injection Molding, injection velocity	<b>200</b>	mm/s	ISO 294

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	<b>120</b>	°C	-
Pre-drying - Time	<b>2 - 3</b>	h	-
Processing humidity	<b>≤0.02</b>	%	-
Melt temperature	<b>280 - 320</b>	°C	-
Mold temperature	<b>80 - 100</b>	°C	-

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Pellets

**Additives**

Release agent

**Special Characteristics**

High impact or impact modified, Transparent

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Other text information**

**Injection molding**

**PREPROCESSING**

Max. Water content: 0.01 - 0.02 %

Drying temperature: 120 °C

Drying time:

Circulating air drying oven (50 % fresh air) 4-8 h

Fresh air dryer (high speed dryer) 2-4 h

Dry air dryer 2-3 h

**PROCESSING**

Melt temperature: 280-320 °C

Mold temperature: 80-100 °C

Use open nozzle.