

Product Texts

Bioresorbablepolymers to enhance the performance of medical devices.

Degradation timeframe: > 2 years

Applications: orthopedic, cardiovascular, wound healing

Inherent viscosity range: 1,13-1,38 dL/g

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	65	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	-62	°C	ISO 11357-1/-2

Characteristics**Special Characteristics**

Sterilizable, Ethylene Oxide (EtO) Sterilization, Gamma irradiation sterilization, Electron beam (e-beam) sterilization

Certifications

Contains renewable resources, Biodegradable, Medical Grade, Drug Master File, Device Master File

Applications

Medical

Regional Availability

Europe