

EMI 362 Z

PC-MEF(x)15

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0055	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2827	MPa	ASTM D 638
Tensile Strength	65.5	MPa	ASTM D 638
Elongation at Break	8	%	ASTM D 638
Flexural Modulus	2827	MPa	ASTM D 790
Flexural Strength	107	MPa	ASTM D 790
Izod Impact notched, 1/8 in	69.4	J/m	ASTM D 256

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	10000	Ohm	ASTM D 257
Volume Resistivity	1	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1350	kg/m ³	ASTM D 792
Moisture Content	0.02	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	121	°C	-
Pre-drying - Time	4	h	-
Melt temperature	277 - 304	°C	-
Mold temperature	71.1 - 121	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Increased electrical conductivity

Features

EMI Attenuation/Shielding

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific