

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	9	cm³/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Melt temperature	260	°C	-

Characteristics

Processing

Other Extrusion

Delivery form

Natural Color

Special Characteristics

Opaque

Features

Scratch Resistant

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa